



## Supplementary Materials

**Table S1.** The Metallic Composition of the Pyrolysis Solid Product

<b>Metals</b>	<b>(mg/kg)</b>
Fe	2,705.42
Co	4.86
Ni	259.91
Cu	17,607.60
Zn	62.58
Al	400.20
Pb	3,604.42
Sn	502.21
Cd	0.37
Ag	4.21
Sb	2.45
Au	0.37
Pd	0.64
Ti	5.08